

Ni 3.0 - 5.0

Code & Specification

Description

BLUME HF44CrMnNi-OA is a 13% Chromium Nitrogen containing martensitic stainless steel self shielded flux cored wire. The complete martensitic microstructure provides excellent tempering stability, wear resistance, excellent heat resistant fatigue and stress corrosion cracking ability.

Applications

BLUME HF44CrMnNi-OA is suitable for surfacing continuous casting roller, as well as for surfacing valve seat, gate valve, wedge valve, safety valve, forming roller, pinch roller, etc.

Mechanical Properties

Hard-Surfacing Hardness (HRC)

40 - 48

Undiluted Weld Metal Analysis (wt%)

\mathbf{C}	Mn	Si	Cr
\leq 0.10	\leq 2.0	≤ 1.0	11.5 - 15.0
Mo	N	Fe	
0.5 - 1.2	0.05 - 0.12	Bal	

Suggested Welding Parameters (DC+)

Diameter

	Volts	Amps	Extension Length
2.4mm (3/32")	26 - 35	250 - 400	25mm - 40mm (1" - 1.5")
2.8mm (7/64")	28 - 35	250 - 450	25mm - 45mm (1" - 1.8")
3.2mm (1/8")	30 - 35	300 - 500	30mm - 50mm (1.2" - 2")

Packaging

15 kgs (33 lbs) [Net Weight] Plastic spools with OD = 270mm (11") or 250 kgs (550 lbs) Drum Packing

Notes